



**OBEIKAN TECHNICAL FABRICS CO. LTD.**

PO Box 1087, Riyadh 11431 Kingdom of Saudi Arabia

Tel: +966 1 2653533 Fax: +966 1 2653438

Website: [www.obeflex.com](http://www.obeflex.com)

Email: [otf@obeikan.com.sa](mailto:otf@obeikan.com.sa)

**TECHNICAL DATA SHEET**

Product Name	OBEFLON_800β™		
Coating	PTFE Coated Glass Fabric		
Base fabric Support	GF-EC3		
	<b>Value</b>	<b>Unit</b>	<b>Test Method</b>
Ends/Picks	13/13	per cm	DIN EN 1049
Yarn	1360	dtex	DIN EN ISO 2060
Weave	L1/1	plain	DIN ISO 9354
Greycloth weight	365	g/m <sup>2</sup>	DIN 53854
Type of Coating	PTFE coated on both sides		
Coated Fabric Weight	800	g/m <sup>2</sup>	DIN 53854
Thickness	0.50~0.55	mm	DIN 53353
Strip Tensile			
Warp (min)	3500	N/5cm	DIN 53354
Fill (min)	3500	N/5cm	DIN 53354
Tear Strength			
Warp (min)	300	N	DIN 53363
Fill (min)	300	N	DIN 53363
Coating Adhesion (min)	60	N/5cm	DIN 53357
Elongation @ break			
Warp			DIN 53354
Fill			DIN 53354
Solar Reflectance (min)	72	%	
Solar Transmission	8 (+/-2)	%	
Available Width (min)	300	cms	DIN EN 22286
Color	Standard color, becomes white after bleaching out		
<b>Fire Performance</b>			
Non-Combustible accdg to	Class A2		DIN 4102
Intermittent Flame	Class A		ASTME - 108
Spread of Flame	Class A		ASTME - 84
	Pass		ASTM - 136
	Pass		NFPA
	Pass		UBC Part IV

Information listed above is based on our general experience and observation and is given in good faith. OTF will not accept any responsibilities with respects to factors outside our knowledge. Values without tolerance statements are values with a tolerance of ±5%